

BAWA FORM B

- BAWAFORM B is class-105 based on modified polyvinyl formal wire enamel and recommended for round and rectangular magnet wires.
- BAWAFORM B has been specially formulated have good flexibility.
- It is suitable for die wiping only round wire 0.5mm to 5mm & upto 40sq.mm rectangular wire.
- BAWAFORM B is UL recognized vide file no. E326858.

Physical Properties

Appearance	Pale Clear Liquid
Solid Content 1g/200°C/1h	23 ± 1%
* Viscosity (in cps)	2200-3300
Flash Point	40°C
Compatibility with thinner	1 : 1

** Viscosity by Viscometer at 23°C

Mechanical Properties

Diameter of bare wire	1.0 mm
Build up of enamel	0.070 mm
Elongation	38%
Flexibility Mandrel Winding (15% pre-stretch 1xd)	OK
Jerk Test	OK
Peel Test (nxd)	175 - 185
Abrasion (Av) (Unidirectional)	12N

Thermal Properties

Heat Shock 1d/180°C/ 30min	OK
Cut Through 220°C / 2min	OK

Chemical Properties

Solvent Resistance	
Pencil Hardness	
Initial	5h
Std. Solvent	4h

Electrical Properties

Break Down Voltage kV	at RT	7
--------------------------	-------	---

Tan Delta

Bending Point °C (solid block)	95-115
-------------------------------------	--------

Please note that all above-mentioned values may be changed according to the machine.

RECOMMENDED THINNER	Thinner W/E	
PACKING:	BAWA FORM B Thinner PW/E	200 Kg in mild steel drums. 21 Kg in mild steel drums.
SHELF LIFE	One year from date of manufacturing if stored in sealed container (at room temperature 25°C).	

This information contained here is best to our knowledge. Company makes no warranty of results and assurance, no obligations or liabilities for the use of any products and process herein. This publication is not to be taken as a license to operate under or recommendation to infringe upon any patents .

HARMAN BAWA (P) LTD.

65, West Avenue Road, Punjabi Bagh West, New Delhi – 110 026

Ph: 011-25222629,25222083 (FAX.) 011-25227237

Web: www.harmanbawa.com | Email: harmanbawa@hbpl.co.in, info@hbpl.co.in