

TECHNICAL DATA SHEET

BAWA 301 is polyester (CLASS 155)

PRODUCT DESCRIPTION

BAWA 301.35 is a class 155 polyester wire enamel. BAWA301.35 is suitable for die and felt . BAWA 301.35 is specially suitable for wire 0.5-2.0mm.

Physical / Mechanical PROPERTIES	
Appearance	Brown colour liquid .
Solid Content (1g/180°C/1h)	35±1%
Size mm	0.05 to 2.
*Viscosity	90-120
Flash Point	40°
Build up of enamel	0.070mm
Diameter of Bare wire	1.0mm
Elongation	36%
Flexibility (Mandrel Winding 15% prestretch 1xd)	OK
Jerk Test	OK
Peel Test	160-180
Abrasion (AV)	12.N

* Viscosity by Ford Cup (B4) at 30°C in sec.

THERMAL PROPERTIES	
Heat Shock (4d/180°C/30min)	OK
Cut Through Temperature (280°C/ 2min)	OK

CHEMICAL PROPERTIES

Solvent Resistance	
Pencil Hardness	
Initial	4h
Std. Solvent	3h

ELECTRICAL PROPERTIES

Breakdown Voltage kV	at RT	9.5kv
-----------------------------	-------	-------

TANGENT DELTA

Bending Point°C (solid block)	115-135	
---	---------	--

Please note that all above-mentioned values may be changed according to the machine.

Recommended Thinner		Thinner W/E
PACKING	BAWA 301	210 kg in mild steel drums.
SHELF LIFE	Thinner W/E	21 kg in mild steel drums.

One year from date of manufacturing if stored in sealed container (at room temperature 25°C).

DISCLAIMER

The values given in this technical data sheet are typical and are intended as a guide only. Actual performance may vary depending on processing conditions, equipment, and wire size. This document does not constitute a product specification. Users should conduct their own tests to determine suitability for the intended application.